



Diamond Oil Active is for those who appreciate an incredibly high level of quality when oiling their wood floors. This exclusive, single-component, low-odour, extremely hard-wearing floor oil is made from the absolutely finest quality materials, is very easy to work with and assures minimal waste. Diamond Oil Active's unique hyper cross linking technology will give your wooden floor a comfortable, non-slip surface that is extremely water repellent and easy to clean and maintain. The oil has a dry matter content of >90% and is suitable for machine-application when oiling untreated, new or newly-sanded wood floors in all species of wood.

- **Resistant to liquids such as water, coffee, tea and wine**
- **Resistant to scratches and marks**
- **Gives the wood a beautiful, breathable surface**
- **Approved for indoor use**



AppArea

For untreated, new or newly-sanded wood surfaces

Work_Descrip_Label

Preparation_Label The wood must be freshly-sanded with grit 120-150 for the final sanding. Product, room and floor temperature must be between 59-86°F. Ensure good ventilation when applying the oil and when it is drying. Wash the floor with WOCA Intensive Wood Cleaner. Leave the floor to dry for at least 8 hours before applying the oil.

Always remember to test on a less visible spot to check the compatibility of the surface with the product.

FinalSanding Grit 120-150

Treatment Thoroughly shake the container of Diamond Oil Active, both before and during use. Containers with different batch numbers should be mixed to avoid colour mismatch. Apply the oil using a short-bristled paint roller (1/4") in an even coat. Leave the oil to penetrate for 10-15 min. If the oil soaks quickly into the wood, apply more oil. Polish the oil into the wood until the floor appears saturated. Use a buffing machine with a white or beige pad. Remove excess oil with dry, lint-free cotton cloths or pads until the surface no longer appears wet.

NoteTxt Any cloths that have been soaked in oil should be stored/disposed of in sealed containers or incinerated due to risk of self-ignition.

DryingTime

DryBefore2Treat 6-12 hours at 68°F.

DryingTime Approx. 24 hours at 68°F.

DryLightUse 12 hours

FullyHard 3-5 days at 68°F.

Rec Do not expose the floor to water or clean it for the first 3-5 days while the oil is hardening. After 3-5 days the floor can be cleaned with WOCA Natural Soap, which gives the surface extra protection.



Techdata_label

Density	0.95 to 0.98 g/cm ³
SolidContent	> 90%
ShelfLife	36M
AppTemp	+59-86°F.
Viscosity	35 to 42 mPa·s [35 to 42 cP].
Consumption	215-270 sq.ft/L.
Colours	9 colors
CleaningTools	With WOCA Solvent.
Storage	+50-77°F. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer (max. +77°F).
AvailPotSizes	8.454 fl.oz. - 84.54 fl.oz.
NonSlip	R9
Migration_Test	EN 71-3:2013
Authorisations	Danish Indoor Climate Labeling IBR: TVOC28/A+, AgBB Z-157.10-198

MaintenanceProd

WeeklyCleanProd	Natural Soap, #511010
MonthlyCareProd	Oil Refreshing Soap, #511210
MaintenanceHdn	Maintenance Oil Diamond Active, #212125
RelatedProducts	Intensive Wood Cleaner, #551525
ApplicationTool	Paint Roller, 4 mm nap, #88004 Paint Roller Handle, 25 mm, #599650 Telescopic Rod, #599651

Contact_Label

WOCA Denmark A/S
Tvæervej 6
DK - 6640 Lunderskov
T +45 9958 5600
info@wocadenmark.com
wocadenmark.com

Disclaimer_Long