



PRODUCT INFORMATION SHEET

Jet Glo[®] Accelerator CM0120975

DESCRIPTION

CM0120975 is a conventional urethane accelerator intended to speed cure, tape time, etc. Urethane accelerators are very reactive and great care must be used in the quantity added. Excess accelerator can cause gassing (solvent pop and microblisters), loss of gloss and haze.

MIXING INSTRUCTIONS

Maximum dosage should be ¼ fluid ounce per ½ gallon of admixed material. This will usually speed the tape time to approximately 2-3 hours at 75°F (24°C). Most commonly used for quick drying times on stripes, registration numbers and logos.

Do not use for overall base colors, metallics, or high temperature or high humidity conditions.

COATING PROPERTIES

Weight Per Gallon:	7.7 lb/gal.
Specific Gravity:	0.93
VOC:	7.6 lb/gal. (909 g/L)
Workable Pot Life: (Limited)	Workable 1 Hour Gelled 2-3 Hours

SHELF LIFE

Shelf Life is only applicable for materials stored in unopened and undamaged containers.

Minimum Storage Temp. 40°F / 4°C
Maximum Storage Temp. 90°F / 32°C

CM0120975: 3 years

USE OF SYSTEMS STATEMENT

Sherwin-Williams Aerospace coatings have been developed and evaluated for use as complete systems. The Aerospace primers have been developed to be compatible with the Jet Glo[®], Acry Glo[®] and Accent[™] polyurethane coatings. Use of products not manufactured by Sherwin-Williams Aerospace as primer replacements is not recommended and could negatively affect coating appearance, inter-coat adhesion, chemical resistance, and durability of the finish. Use a complete Sherwin-Williams Aerospace system to ensure the long-term integrity of the coating.

HEALTH AND SAFETY INFORMATION

Consult the Material Safety Data Sheets for product information regarding health, physical and environmental hazards, handling precautions and "First Responder" first-aid recommendations.

PRODUCT INFORMATION

Please contact your Sherwin-Williams Aerospace Distributor or Representative for more information.

NOTE: Product Information Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Information Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, The Sherwin-Williams Company cannot make any warranties as to the end result.